Code: B617 2026/10 EN

Biocalce Intonachino Tipo “00”

Breathable finishing product based on NHL 3.5 natural hydraulic lime for polished finishing of plasters/renders.

Biocalce Intonachino Tipo “00” is a breathable finishing product suitable for the polished finishing of plasters/renders, for dehumidifying systems and for historical restorations, as the final stage of Biocalce cycles.



1. **Cement-free**
2. **Highly breathable**
3. **Long workability and excellent finishing coat**
4. **Reduces formaldehyde (standard ISO 16000-23)**
5. **Bacteriostatic and fungistatic product (standard ISO 846 A/B/C)**
6. **For internal and external use**

kerakoll

Areas of application

→ Intended use
It is particularly suitable for polished finishings on plastered/rendered surfaces. For internal and external use. It ensures high levels of porosity, hygroscopicity and breathability – essential requirements for maintaining a comfortable living environment and healthy indoor conditions.

Cement-free. Thanks to its formulation based on natural hydraulic lime, it is suitable for historical restorations and conservative interventions in full respect of the existing structures and original materials.

Do not use on dirty, non-cohesive, powdery substrates; on not suitably-prepared substrates; on old paints or lime putty coverings; on substrates with a lot of interstitial salt deposits. Do not apply directly to gypsum-based plasters/renders; if that is the case, prior treatment with Rasobuild Consolidante is required.

Instructions for use

→ Preparation of substrates
The substrate must be clean and solid, free from loose debris, dust and mould. Old plasters must be dry, in good condition, compact and cleaned carefully to remove any remaining traces of previous processes (lime putty coverings, old finishing coats, etc.). Scratch off the surfaces of new plaster coats with a metal scraper to remove the surface cement slurry, to make it easier to then lay the finish layer without air bubbles forming. Before finishing, always wet substrates.

→ Preparation
To prepare Biocalce Intonachino Tipo “00” mix one 20 kg bag with about 10 l of clean water. The mixture is obtained by pouring water into the container and then gradually adding the powder. The mixing process can be performed in a cement mixer, in a bucket (working manually or with a low-rev, mechanical stirring device) or using a continuous mixer until a smooth and lump-free mortar is obtained. Use all of prepared mixture; do not reuse it in subsequent mixings. store the product in places protected against the heat in summer months and against the cold during the winter. Use running water not subject to the influence of outside temperatures. Adding cement in any quantity would impair the quality of the mortar.

→ Application
Biocalce Intonachino Tipo “00” is as easy to apply with a smooth spreader as a conventional gypsum-based finishing product.
Prepare and dampen the plaster/render surface then apply a first coat of the product using a smooth spreader. Press down hard to ensure adhesion and to force the air out of the pores. Then apply the next coats until the required finish is obtained.
Allow the hardened product to cure and keep it moistened during the first 24 hours. In case of heterogeneous surfaces, it is recommended to embed the Rinforzo V 40 or Rinforzo V 50 fibreglass reinforcing mesh into a first coat of freshly applied Biocalce Intonachino Fino, pressing it down with a spreader.
When curing has been completed, apply a second coat of Biocalce Intonachino Fino and continue with subsequent coats of Biocalce Intonachino Tipo 00 until the desired finishing is achieved.

→ Cleaning
Tools can be cleaned with water before the product hardens.

Special notes

→ **Biocalce Intonachino Tipo “00” is a non-pigmented natural hydraulic lime product, hence the colour may vary from production batch to batch.**

→ **Furthermore, being a mineral product, the colour of the hardened, dried finish will vary depending on substrate absorption and weather conditions during application.**

Certificates and marks

* *Émission dans l’air intérieur Information sur le niveau d’émission de substances volatiles dans l’air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).*

Abstract

Polished surface finishing will be carried out using a breathable finishing product made of NHL 3.5 natural hydraulic lime containing fine pure white Carrara marble inert materials, 0–100 µm grading, according to standard EN 1015-1, such as Biocalce Intonachino Tipo “00” by Kerakoll. Certified technical characteristics: adhesion to support ≥ 0.3 N/mm² according to standard EN 1542, reaction to fire class A1, volatile organic compound emissions EC1 Plus GEV-Emicode-certified, bacteriostatic and fungistatic according to standard ISO 846 A/B/C, helps to reduce formaldehyde according to standard ISO 16000-23, compliant with the CAM - (Minimum Environmental Criteria) requirements of paragraphs 1.3.2, 2.6.3, 3.2.4, 2.3.17, 2.5.4, 2.4.1, 3.2.6 and 3.2.2 of the Italian Ministerial Decree 24/11/2025, with EPD environmental certification according to standards ISO 14025:2006 and EN 15804:2012+A2:2019/AC:2021.
Biocalce Intonachino Tipo “00” coverage: ≈ 1 kg/m² per mm of thickness.

Technical Data compliant with Kerakoll Quality Standard		
Type of mortar	mortar for internal, external finishing layers	
Chemical nature of binder	natural hydraulic lime NHL 3.5 / CL 90-S	EN 459-1
Grading	0 – 100 µm	EN 1015-1
Apparent density of powder	≈ 0.871 kg/dm³	UEAtc
Shelf life	≈ 12 months from production in the original sealed packaging, protect from humidity	
Pack	20 kg bags	
Mixing water	≈ 10 l / 1 bag 20 kg	
Consistency of wet mortar	≈ 196 mm	EN 1015-3
Apparent density of wet mortar	≈ 1.60 kg/dm³	EN 1015-6
Apparent density of dry, hardened mortar	≈ 1.42 kg/dm³	EN 1015-10
pH of the mixture	≥ 12	
Temperature range for application	from +5 °C to +30 °C	
Max thickness	≈ 2 mm	
Coverage	≈ 1 kg/m² per mm of thickness	

Values taken at +20 ± 2 °C, 65 ± 5% R.H. and no ventilation. Data may vary depending on specific conditions at the building site.

Performance relating to indoor environmental quality			
VOC – Volatile organic compound emissions			
Conformity	EC 1 plus GEV-Emicode		GEV certified 2755/11.01.02
Formaldehyde reduction – standard ISO 16000-23			
The product helps to reduce formaldehyde levels			
Dilution of indoor pollutants *			
	Flow	Dilution	
Toluene	318 µg m²/h	+4%	JRC method
Pinene	413 µg m²/h	+4%	JRC method
Formaldehyde	7369 µg m²/h	na	JRC method
Carbon dioxide (CO_2)	585 mg m²/h	+4%	JRC method
Humidity (Humid Air)	84 mg m²/h	+18%	JRC method

*Tests carried out in-house in accordance with a test method developed in collaboration with the JRC: Joint Research Centre – European Commission, Ispra (Varese, Italy) – to measure the reduction of polluting substances in indoor environments (Indoortron Project). Flow and speed in proportion to a standard cement-based finishing product (3 mm).

HIGH-TECH

Performance characteristic	Test methods	Requirements of standard	Performance
Compressive strength after 28 days	EN 1015-11	Reference class	≥ 1 Mpa
Substrate adhesion	EN 1015-12	None	≥ 0.3 Mpa
Reaction to fire	EN 13501-1	Euroclass	A1

Values taken at +20 ± 2 °C, 65 ± 5% R.H. and no ventilation. Data may vary depending on specific conditions at the building site.

Warning

→ Abide by any standards and national regulations
→ use at temperatures between +5 °C and +30 °C
→ make sure the substrate is not frozen
→ protect surfaces from direct sunlight and wind
→ do not apply on dirty or loose surfaces
→ dampen walls before application
→ allow the hardened product to cure and keep it moistened during the first 24 hours
→ if necessary, ask for the safety data sheet
→ for any other issues, contact the Kerakoll Worldwide Global Service +39 0536 811 516 - globalservice@kerakoll.com

Kerakoll Quality System ISO 9001 CERTIFIED IT10/0327
Kerakoll Quality System ISO 45001 CERTIFIED 18586-I

This information was last updated in October 2026; please note that additions and/or amendments may be made over time by KERAKOLL SpA; for the latest version, see www.kerakoll.com. KERAKOLL SpA shall therefore be liable for the validity, accuracy and updating of information provided only when taken directly from its institutional website. The technical data sheet given here is based on our technical and practical knowledge. As it is not possible for us to directly check the conditions of your building site and the execution of the work, this information represents general indications that do not bind Kerakoll in any way. Therefore, it is advisable to perform a preliminary test to verify the suitability of the product for your purposes.

Kerakoll Spa
via dell'Artigianato 9
41049 Sassuolo - MO

+39 0536.816.511
info@kerakoll.com

www.kerakoll.com