Code: B639 2026/10 EN

Biocalce Muratura Fino

Breathable mortar based on NHL 3.5 natural hydraulic lime for bedding, dubbing out and structural strengthening of masonry.

Biocalce Muratura Fino is an M10 class mortar specifically intended for the breathable building, recovery, fragment-filling and structural reinforcement of load-bearing masonry and infill masonry in seismic zones.



1. **Cement-free, suitable for historical restorations**
2. **Advanced pozzolanic behaviour with Min3Ra Technology**
3. **M10 class according to standard 998-2**
4. **Long workability and adjustment times when laying blocks**
5. **Reduces formaldehyde (standard ISO 16000-23)**
6. **Bacteriostatic and fungistatic product (standard ISO 846 A/B/C)**
7. **For internal and external use**

kerakoll

Areas of application

→ Use
Breathable building, recovery and fragment-filling of interior and exterior hollow clay block, brick, tufa, stone, and mixed-material load-bearing masonry structures and infill masonry also in seismic zones. Biocalce Muratura Fino is particularly suitable as a construction mortar, even in seismic areas, for rough coating and fragment-filling of masonry in Building for Wellness, ensuring compliance with the key parameters of porosity, hygroscopicity and breathability – essential elements for creating a healthy environment. Biocalce Muratura Fino is suitable for reconstruction work in historical restoration projects, where the choice of traditional materials such as natural lime guarantees conservation interventions in full respect of the existing structures and original materials.

Do not use on dirty, non-cohesive, powdery substrates, and on substrates with interstitial salt deposits.

Instructions for use

→ Preparation of substrates
Masonry structures must be clean and solid, free from loose debris, dust and mould. Old walls must be carefully cleaned and remaining traces of previous processes removed (lime putty coverings, old finishing coats, etc.) as well as any interstitial salt deposits which could impair adhesion. Remove inconsistent rendering mortars from between the stones. Use Biocalce Muratura Fino and the fragment-filling and/or break-fill techniques to rebuild missing sections of the wall and restore an even surface. Always wet substrates before reconstruction work with Biocalce Muratura Fino.

→ Preparation
To prepare Biocalce Muratura Fino mix one 25 kg bag with about 4.8 l of clean water. The mixture is obtained by pouring water into the container and then gradually adding the powder. The mixing process can be performed in a cement mixer, in a bucket (working manually or with a low-rev, mechanical stirring device) or using a continuous mixer until a smooth and lump-free mortar is obtained. Use all of prepared mixture; do not reuse it in subsequent mixings. store the product in places protected against the heat in summer months and against the cold during the winter. Use running water not subject to the influence of outside temperatures. Adding cement in any quantity would impair the quality of the mortar.

→ Application
Biocalce Muratura Fino can be easily applied with a trowel or plastering machine like a normal mortar. Always wet substrates before reconstruction work with Biocalce Muratura Fino. Apply the mortar using a trowel to create the mortar bed then place the building block into it, pressing lightly with circular movements until it is correctly aligned and at the right depth; remove any excess mortar on the front of the masonry using the trowel.

→ Cleaning
Tools can be cleaned with water before the product hardens.

Special notes

→ Allow the mortar to dry fully before placing loads on load-bearing masonry structures. dampen bricks before placing. Always lay a full mortar bed, allowing the mortar to flow through joints during adjustment. Use a trowel to remove the excess mortar and leave the remaining level flush with the wall.

→ Biocalce Muratura Fino is a non-pigmented natural hydraulic lime product, hence the colour may vary from production batch to batch.

→ Furthermore, being a mineral product, the colour of the hardened, dried mortar will vary depending on substrate absorption and weather conditions during application.

Certificates and marks



** Émission dans l'air intérieur Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).*

Abstract

Breathable building and fragment-filling of interior and exterior hollow clay block, brick, tuff and natural stone masonry will be carried out using a breathable mortar based on NHL 3.5 natural hydraulic lime, such as Biocalce Muratura Fino by Kerakoll.
Certified characteristics of the mortar: the mortar is CE-marked according to standard EN 998/2 G/M10, initial shear strength ≥ 0.15 N/mm² according to standard EN 1052-3, capillary water absorption < 0.7 kg/(m² · min$^{0.5}$) according to standard 1015-18, reaction to fire class A1, volatile organic compound emissions EC1 Plus GEV-Emicode-certified, bacteriostatic and fungistatic according to standard ISO 846 A/B/C, helps to reduce formaldehyde according to standard ISO 16000-23, compliant with the CAM - (Minimum Environmental Criteria) requirements of paragraphs 1.3.2, 2.6.3, 3.2.4, 2.1.2, 2.6.6, 2.3.17, 2.5.4, 2.4, 2.4.1, 3.2.6 and 3.2.2 of the Italian Ministerial Decree 24/11/2025, with EPD environmental certification according to standards ISO 14025:2006 and EN 15804:2012+A2:2019/AC:2021. Application can be done by hand or by machine.
Coverage Biocalce Muratura Fino: ≈ 1.7 kg/dm³.

Technical Data compliant with Kerakoll Quality Standard		
Type of mortar	performance-guaranteed masonry mortar for general purpose use (G) in external applications subject to structural requirements	EN 998-2
Chemical nature of binder	natural hydraulic lime NHL 3.5	EN 459-1
Grading	0 – 1.5 mm	EN1015-1
Apparent density of powder	≈ 1.47 kg/dm³	UEAtc
Shelf life	≈ 12 months from production in the original sealed packaging, protect from humidity	
Pack	25 kg bags	
Mixing water	≈ 4.8 l / 1 x 25 kg bag	
Consistency of wet mortar	≈ 178 mm	EN1015-3
Apparent density of wet mortar	≈ 2.01 kg/dm³	EN 1015-6
Apparent density of dry, hardened mortar	≈ 1.76 kg/dm³	EN 1015-10
pH of the mixture	≥ 12	
Temperature range for application	from +5 °C to +35 °C	
Coverage	≈ 1.7 kg/dm³	

Values taken at +20 ± 2 °C, 65 ± 5% R.H. and no ventilation. Data may vary depending on specific conditions at the building site.

Performance			
VOC Indoor Air Quality (IAQ) - Volatile organic compound emissions			
Conformity	EC 1 plus GEV-Emicode		GEV certified 2749/11.01.02
Formaldehyde reduction – standard ISO 16000-23			
Helps to reduce formaldehyde			ISO 16000-23
Dilution of indoor pollutants *			
	Flow	Dilution	
Toluene	124 µg m²/h	+28%	JRC method
Pinene	202 µg m²/h	+25%	JRC method
Formaldehyde	4698 µg m²/h	na	JRC method
Carbon dioxide (CO_2)	29 mg m²/h	+31%	JRC method
Humidity (Humid Air)	14 mg m²/h	na	JRC method
HIGH-TECH			
Performance characteristic	**Test methods**	**Requirements of EN 998-2**	**Performance**
Compressive strength after 28 days	EN 1015-11	Reference class	M10
Initial shear strength	EN 1052-3	table value	≥ 0.15 N/mm²
Water absorption through capillary action	EN 1015-18	categories	< 0.7 kg/(m² · $min^{0,5}$)
Water vapour permeability coefficient (µ)	EN 1015-19	Declared value	15 ≤ µ ≤ 35
Chloride content	EN 1015-17		< 0.08% Cl
Thermal conductivity ($\lambda_{10, dry}$)	EN 12667	table value	0.82 W/mK
Specific heat capacity (Cp)	measured with heat exchange analyser		1.70 (10^6 J/m³K)
Durability (freeze-thaw)	998-2		evaluation based on regulations applicable to mortar in the country of use
Reaction to fire	EN 13501-1	Euroclass	A1

Values taken at +20 ± 2 °C, 65 ± 5% R.H. and no ventilation. Data may vary depending on specific conditions at the building site.
* Tests carried out in-house in accordance with a test method developed in collaboration with the JRC: Joint Research Centre – European Commission, Ispra (Varese, Italy) – to measure the reduction of polluting substances in indoor environments (Indoortron Project). Flow and speed in proportion to a standard construction mortar (1.5 cm).

Warning

→ Abide by any standards and national regulations
→ protect surfaces from direct sunlight and wind
→ moisten bricks and substrates before application
→ if necessary, ask for the safety data sheet
→ for any other issues, contact the Kerakoll Worldwide Global Service +39 0536 811 516 - globalservice@kerakoll.com

Kerakoll Quality System ISO 9001 CERTIFIED IT10/0327

Kerakoll Quality System ISO 45001 CERTIFIED 18586-I

This information was last updated in October 2026; please note that additions and/or amendments may be made over time by KERAKOLL SpA; for the latest version, see www.kerakoll.com. KERAKOLL SpA shall therefore be liable for the validity, accuracy and updating of information provided only when taken directly from its institutional website. The technical data sheet given here is based on our technical and practical knowledge. As it is not possible for us to directly check the conditions of your building site and the execution of the work, this information represents general indications that do not bind Kerakoll in any way. Therefore, it is advisable to perform a preliminary test to verify the suitability of the product for your purposes.

Kerakoll Spa
via dell'Artigianato 9
41049 Sassuolo - MO

+39 0536.816.511
info@kerakoll.com

www.kerakoll.com