
MAPELUX LUCIDA

Cross-linked, high-strength shiny metallic wax





WHERE TO USE

Mapelux Lucida is used inside buildings for civil use, such as shops, showrooms, apartments, offices, etc. for protecting floors made using the **Mapefloor System** subject to particularly intense use, or to make maintenance operations of the finishing treatment on floors made using **Ultratop** easier.

Some application examples

- Protective treatment of resin floors made using the **Mapefloor System** inside buildings for civil use.
- Protective treatment of self-levelling floors made using **Ultratop** in environments for civil use, such as showrooms, shops and apartments.
- Protective treatment of decorative floors made using **Ultratop** and natural aggregates, after application of a suitable finishing treatment, in environments for civil use, such as showrooms, shops and apartments.

TECHNICAL CHARACTERISTICS

Mapelux Lucida is a shiny, metallic wax characterised by its high resistance to traffic and frequent cleaning, even if strong detergents are used.

Thanks to the cross-linked structure which binds all the components, the **Mapelux Lucida** film is easy to clean and marks and stains left by traffic may be removed by a simple washing cycle.

Mapelux Lucida is extremely fluid and is easy and quick to spread on the surface.

RECOMMENDATIONS

Do not apply if the temperature is lower than +10°C.

APPLICATION PROCEDURE

Preparation of the substrate

Before applying **Mapelux Lucida**, wait at least 24 hours after laying floors using the **Mapefloor System**. On surfaces in **Ultratop** which have had a successive finishing treatment, only lay **Mapelux Lucida** after the said treatment has completely dried.

Application of the product

Mapelux Lucida must be applied in two crossed passes, to obtain good protection of the surface.

Spread the first coat of **Mapelux Lucida** uniformly using a special wax spreader. Once the first coat has completely dried, spread the second coat at right-angles to the first coat.

CLEANING

Tools and equipment used to apply **Mapelux Lucida** may be cleaned with water after use.

CONSUMPTION

50 g/m².

PACKAGING

Mapelux Lucida is available in 10 kg cans.

STORAGE

Mapelux Lucida can be stored for 12 months in its original packaging at a temperature between +10°C and +30°C. Protect from frost.

SAFETY INSTRUCTIONS FOR PREPARATION AND APPLICATION

Instructions for the safe use of our products can be found on the latest version of the Safety Data Sheet, available from our website www.mapei.com.
PRODUCT FOR PROFESSIONAL USE.

TECHNICAL DATA (typical values)

PRODUCT IDENTITY	
Appearance:	emulsion
Colour:	white
Density:	1.036 g/cm³
Dry substances content:	22 ± 1 %
Active contents:	30 ± 1 %

APPLICATION DATA (at +23°C and 50% R.H.)	
Application temperature range:	from +10°C to +30°C
pH:	8.4 ± 0.2

WARNING

Although the technical details and recommendations contained in this product data sheet correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical application: for this reason, anyone who

intends to use the product must ensure beforehand that it is suitable for the envisaged application: in every case, the user alone is fully responsible for any consequences deriving from the use of the product.

Please refer to the current version of the Technical Data Sheet, available from our website www.mapei.com

LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement or replace requirements per the TDS in force at the time of the MAPEI product installation.

The most up-to-date TDS can be downloaded from our website www.mapei.com.

ANY ALTERATION TO THE WORDING OR REQUIREMENTS CONTAINED OR DERIVED FROM THIS TDS EXCLUDES THE RESPONSIBILITY OF MAPEI.

Mapei S.p.A.

Via Cafiero, 22, 20158, Milano

+39-02-376731 www.mapei.com mapei@mapei.it

2041-2-2023 gb

Any reproduction of texts, photos and illustrations published here is prohibited and subject to prosecution