
PROFILPAS S.P.A.
VIA EINSTEIN, 38 35010 CADONEGHE (PADOVA)
ITALY
TEL. +39 049 8878411 +39 049 8878412
FAX. +39 049 706692
EMAIL: INFO@PROFILPAS.COM



Profiles for floors of different height

Cerfix® Pronivel P

Description

PRONIVEL P is a range of anodised aluminium, natural brass and polished or brushed stainless steel edging profiles with a sloping shape studied specifically to transition between different levels when laying floors of the same or different type.
They create a step-free join between different level floor sections.
This profile is equally effective when laid over a pre-existing floor.

Materials

Anodized aluminium

Al-Mg-Si aluminium, heat-treated in T6 (6060 T6).
The profiles are made by extrusion then anodized with a ≥ 15 µm thick layer.
They present a strong resistance to chemical and atmospheric agents. When wet, concrete and its derivatives produce alkaline substances which can corrode metal (forming aluminium hydroxide) when allowed to react with the surface. For this reason, the visible surface of the profile must be quickly and delicately cleaned to remove any concrete, adhesive or grouting substances and detergents.
Anodized surfaces can become ruined through wear and foot traffic (profiles used on floors) and the original finish lost as a result.

Stainless steel

AISI 304 - DIN 1.4301
Especially resistant to the main chemical and atmospheric agents, to lime, mortar, tile adhesives and cleaning products.
Also recommended for use in food industries, hospitals, external environments in general, etc.

Natural brass

Alloy CW624N UNI EN 12167
The profiles are made by extrusion.
Resistance to chemical agents and mechanical stress is good. Parts of the brass in contact with the air are subject to oxidation, producing a film on the surface. In the presence of extreme humidity or corrosive agents, brass will oxidise quickly and marks may appear on the surface. Where necessary, it can be restored to its natural state with abrasives or special polishes.

General note on metals

Aluminium and brass are not resistant to all chemical compounds. Consequently, contact with particularly aggressive products like hydrochloric acid (HCl) and phosphoric acid (H3P04) should be avoided.
Products generally used to clean stone, ceramic and porcelain tiles, such as muriatic acid, ammonia and bleach, damage the surface finish on the metal and can cause intense corrosion. Moreover, any residues of concrete, adhesive, and grouting materials must always be removed from the surface of the profiles as quickly and delicately as possible.
If adhesive tape is used to cover the profile, it must not be left any longer than an hour.

PROFILPAS S.P.A.
VIA EINSTEIN, 38 35010 CADONEGHE (PADOVA)
ITALY
TEL. +39 049 8878411 +39 049 8878412
FAX. +39 049 706692
EMAIL: INFO@PROFILPAS.COM

Fixing

Fixing with adhesive

Remove the profile from the packaging.
Check that the thickness of the covering/flooring to be laid is not greater than the dimension of the profile (see label).
Where present, also remove any protection (protective and/or shrink-wrapped film) added to protect the finish.
Measure the length required and cut the profile to this length using an appropriate tool.
Level the adhesive on the laying surface using a toothed spreader.
Place the profile in position and level it with the covering laid previously.
Lay the covering delicately, making sure it is flush with the profile and leaving the right space for a grout line (usually 1-2mm).
Fill any gaps left between the covering and the profile with a suitable grout.
Remove any excess grout, adhesive, solvents etc. with a soft sponge and water within ten minutes of application.

Care and maintenance

Care and maintenance procedures for the materials used to make these profiles depends largely on the type of alloy and/or finish used.
The instructions provided below describe the operations to be performed on the profile to restore it as much as possible to its original condition.
The purpose of this document is to provide as many general indications as possible to guide you on when and how to clean the product, but they should also be verified on a case-by-case basis.
It should be pointed out there are specific responsibilities in each part of the product's life cycle, starting from when it is installed the first time.

Aluminium

No special maintenance is required and aluminium products can be easily treated with colourless alcohol in a water solution or using ordinary detergents, provided they do not contain acid (hydrochloric or hydrofluoric).
Detergent products made by multiple manufacturers and sold under a variety of commercial brands can generally be used for cleaning.

Generally speaking, there are three types of products:

- Alkaline
- Neutral
- Acid

For cleaning purposes, we recommend using a neutral detergent diluted in water then rinsing with water only, using a non-abrasive sponge and/or cloth to avoid scratching and/or damaging the anodized surface.

During cleaning, the following aspects must be kept in mind at all times:

- Do not use acid or alkaline detergents because they could damage the aluminium;
- Do not use products and/or abrasive materials;
- Do not use organic solvents on painted surfaces;
- Do not use detergents without first checking their chemical composition;
- Do not apply detergents straight onto the surface to be cleaned;
- Surfaces must be “cold” (max T°= 30°C) during cleaning and not exposed to direct sunlight;
- Detergents used in cleaning must also be “cold” (max T° = 30°C) and steam sprays should not be used.

In any case, the final stage in the cleaning process is always sufficient rinsing of the parts treated with water. They must then be immediately dried using soft fabric or leather cloths. Polishes or similar products are not required.
Clean profiles carefully as soon as required, following the instructions on the product package, to prevent any residues of concrete, grout or similar substances from attacking the surface.

Stainless steel

Stainless steel surfaces can be polished with suitable, widely available products.
Stainless steel is easy to clean and extremely hygienic; the smooth, non-porous surface makes the adhesion and survival of bacteria and/or other micro-organisms.
To keep stainless steel perfectly maintained, there are just a few simple rules: wash with soap and warm water, rinse well then dry with a soft cloth.
For surfaces exposed to atmospheric agents and attack, we recommend cleaning the stainless steel profile regularly to maintain the surface unaltered and prevent corrosion.
Surfaces with a brushed finish should always be cleaned in the direction of the brushing and not at an angle to it.
In the event of scratches, use a detergent/polish made specifically for stainless steel, and a soft cloth.

PROFILPAS S.P.A.
VIA EINSTEIN, 38 35010 CADONEGHE (PADOVA)
ITALY
TEL. +39 049 8878411 +39 049 8878412
FAX. +39 049 706692
EMAIL: INFO@PROFILPAS.COM

For cleaning, do not use any of the following:

- detergents containing hydrochloric acid (also known as muriatic acid), hydrofluoric acid or bleach; avoid direct contact on surfaces with detergents containing chlorides, unless the contact is short and the surface is well-rinsed afterwards.
- abrasive powdered detergents which could damage the surface finish of the profile.

Do not leave mild steel objects or utensils (like brushes or steel wool normally used to remove residues of mortar or similar products) in contact with stainless steel profiles for extended lengths of time. They could transfer iron particles (contamination) and trigger rust on the surface.
Do not leave damp cloths or sponges for extended lengths of time on the stainless steel surface to prevent the formation of unsightly water marks.

Brass

Brass does not require special maintenance: it can be easily cleaned with alcohol diluted in water or ordinary detergents, provided they are not acid-based. Water can be used with added neutral detergents and the final rinse with water alone. Use non-abrasive sponges or cloths which will not scrape the surface. Use polishes that are commonly available.

Fire prevention measures


In the event of fire, use chemical fire extinguishers, dry sand or solid extinguishing agents.

Notes:


These profiles must be handled with caution, being careful to wear suitable gloves to prevent injury and/or cuts to the hands.
The instructions and specifications provided here are the product of our experience but are only a guide, should not be considered exhaustive and must be confirmed by extensive practical applications.
Profilpas declines any responsibility for damage to people or things resulting from improper use of the product.
Users must establish for themselves if the product is suitable for the required used and they bear full responsibility for any incorrect installation of the material.

PROFILPAS S.P.A.
VIA EINSTEIN, 38 35010 CADONEGHE (PADOVA)
ITALY
TEL. +39 049 8878411 +39 049 8878412
FAX. +39 049 706692
EMAIL: INFO@PROFILPAS.COM

Pronivel P



PA/4,5 PA/8 PA/10 PN/10 PA/11 PA/12,5 - PN/12,5 PA/14 - PN/14



PNI/8 - PNIS/8 PNI/10 - PNIS/10 PNI/11 - PNIS/11 PNI/12,5 - PNIS/12,5 PNI/15 - PNIS/15 PNI/20 - PNIS/20

PRONIVEL P

length = 270 cm - pack 10 pcs			H						
ART.	**finishing**		**4,5**	**8**	**10**	**11**	**12,5**	**14**	**15**	**20**
ALUMINIUM										
PA/	silver anodised		93175	93181	93182	93185	93183	93184	-	-
STAINLESS STEEL										
PNI/	polished stainless steel AISI 304 DIN 1.4301		-	93092	93094	93090	93096	-	93098	93100
PNIS/	satin stainless steel AISI 304 DIN 1.4301		-	93093	93095	93091	93097	-	93099	93101
BRASS										
PN/	natural brass		-	-	93122	-	93123	-	-	-

individually packed